



## Material Data Sheet

## PC Film/Sheet Products

### 产品描述 Description:

- VM: Velvet/Matte (Equivalent to Lexan 8B35/ DE 6-2)**
- VG: Velvet/Gloss (Equivalent to Lexan 8A35/ DE 6-1)**
- MG: Matte/Gloss (Equivalent to Lexan 8A13/ DE 1-4)**
- FVM: Fine Velvet/Matte(Equivalent to 832/ DE 4-4)**

VM, VG, MG, FVM are textured polycarbonate film which is served daily use of PC film in local and overseas customers. With the use of the world brand PC resin, the surface textures also have mar resistance. They are widely used for screen-printing for automotive, labels, membrane switches, overlays, automotive dials/ speedometer, thermoforming, punching, IMD, etc.

### 物性表 Typical Property Table

特性 Property	测试方法 Test Method	单位 Units	测试值 Test value
<b>物理性 PHYSICAL</b>			
比重 Specific Gravity	ASTM D792	g/cm <sup>3</sup>	1.2
透光率 Light Transmissivity	ASTM D1003	%	80~88
雾度 Haze	ASTM D1003	%	80-90
平均吸水率 Water Absorption Equilibrium, 24 hrs	ASTM D570	%	0.23
<b>机械性 MECHANICAL</b>			
拉伸强度 Tensile Strength	ASTM D882	psi	8,800
	ISOR1184-1987	MPa	60
极限延伸率 Elongation at break	ASTM D882	%	>90
冲击强度 Impact Strength @ 10mils	JIS-K6745	In-lbs	120
<b>耐温性 THERMAL</b>			
维卡软化点 Vicat Softening Point 120 °C/hr, 10N load	ISO 306	°C	151
<b>电气性 ELECTRICAL</b>			
介电强度 Dielectric Strength (@ 10mils)	ASTM D149	V/mil	1,700
体积绝缘 Volume Resistivity@25°C,50%RH	ASTM D257	Ω.cm	10 <sup>16</sup>
表面绝缘 Surface Resistivity@25°C,50%RH	ASTM D257	Ω	10 <sup>15</sup>
<b>阻燃性 FLAMMABILITY</b>			
UL 防火等级 UL Flammability @ ≥10 mils	UL94		V-2
		@ < 10 mils	VTM-2
厚度公差 Thickness tolerance <0.250mm(0.010")		%	±10%
			≥0.250mm(0.010")

**Note: The values in the typical property table are for reference only. For further requirements, please contact us.**